



KEIM RESTAURO FIXATIV

1. Product Information

Silicate binding agent for use with the Keim Restauro Lasur colour wash system. Reacts chemically with the surface.

2. Field Of Application

Modern and historic render/stone surfaces, including brickwork and reconstituted stone and any cementitious or lime based mineral substrates in conjunction with the Keim Restauro Lasur system.

3. Product Characteristics

- Water vapour permeable
- Consolidates the surface
- Odourless
- Non toxic

Material Data:

Density: Q = 1.17 g/cm₃
Flash Point non flammable

4. Application

Substrate Preparation:

All loose and flaking paint should be removed using wire brushes and broad bladed scrapers to get back to a sound edge. When all surfaces are clean, sound, wind dry, dust free and free from all surface contaminants, decoration using Keim Mineral Paints may proceed.

Decoration:

A typical specification would be a two coat Keim Restauro Lasur system, the first coat to be diluted with Keim Restauro Fixativ to the required level, applied by brush and worked well into all surfaces. After a minimum period of 12 hours a final coat of Keim Restauro Lasur may be applied, again diluted to the required level with Keim Restauro Fixativ.

Air and surface temperature >5°C

Consumption:

For two coats between 0.1-0.2 kg per square metre for Keim Restauro Lasur and 0.1- 0.4 lt per square metre Keim Restauro Fixativ.

Tools:

Clean immediately after use with water.

5. Packaging

5 & 25 kg containers

6. Storage

Approx. 12 months, if kept cool, but frost free in tightly closed containers.

7. Identification Ref. Ordinance Of Dangerous Materials

Not applicable

8. Danger Class In Goods traffic

Not applicable

9. Safety Instructions

Cover surfaces, which are not to be painted, in particular glass, natural stone, ceramics etc. Protect the eyes and skin from splashes. Keep out of reach of children.

Refer to COSHH data sheet.