



## KEIM BOFIMEX 610

### 1. Product Information

Two component clear permanent anti-graffiti system primer coat for use with the Keim Anti-graffiti 620 clear and Keim Anti-graffiti 630 coloured systems.

### 2. Field Of Application

All non-treated surfaces internally and externally, particularly mineral such as brick, render, sand-lime bricks, various types of natural stone, fair faced concrete etc. Surfaces decorated with Keim Mineral Paints can be treated 7 days after application.

### 3. Product Characteristics.

- Does not yellow
- Highly resistant to oils, grease, many chemicals and solvent
- Chip proof and impact resistant

#### **Material Data:**

Density:	1.30-1.40 g/ml (20°C)
Flash Point:	(A) 27°C (B) 27°C
Colour:	Clear
Viscosity:	5.000-10.000 mPas (20°C)
Mixing ratio:	80 parts component A 20 parts component B
Pot life:	approx. 6 hours

### 4. Application

#### **Substrate Preparation:**

Any surfaces decorated with Keim Mineral Paints should be left for a minimum period of 7 days prior to any treatment taking place. All surfaces should be washed down with clean cold water to remove all surface dirt and dust.

Apply a first coat of Keim Anti Graffiti Primer PU 610 which is a two part pack. Components A & B should be well mixed by mechanical mixer and applied by spray or roller. After a minimum period of 24 hours a final coat of Keim Anti Graffiti Transparent PU 620 or Keim Anti Graffiti Coloured PU 630 should be applied.

Do not treat the first 20-30 cm wall height from ground level.

#### **Consumption:**

Approx. 0.1 kg/m<sup>2</sup>

#### **Tools:**

All tools and equipment to be cleaned using Keim Anti-Graffiti PU Thinner 660.

#### **Temperature:**

Working temperature: 5-35°C

### 5. Packaging

5 kg containers

### 6. Storage

Approx. 12 months, if kept cool but frost free in tightly closed containers. Store dry, do not expose to direct heat.

### 7. Working Instruction

Do not smoke when processing, do not inhale spray dust. Take precautions that it does not get in to canalisation.

### 8. Identification Ref Ordinance Of Dangerous Material

Not applicable

### 9. Danger Class In Goodstraffic

Classification: 3.2  
Packing group: II  
UN: 1263

### 10. Safety Instructions

Cover surfaces which are not to be treated, in particular plants, etc. Protect the eyes and skin from splashes. Keep out of reach of children.

Refer to appropriate COSHH data sheets.